

## CPAR W-50

## VERY LONG-CHAIN CHLORINATED PARAFFINS

PROPERTY	TYPICAL RESULT
Color, Gardner	2
Chlorine, % by Weight	47
Specific Gravity, 25 C	1.21
Density, lbs/gal	10.1
Viscosity, SUS @ 210 F	300
Viscosity, SUS @ 100 F	15000
Viscosity, cSt @ 100 C	70
Viscosity, cSt @ 40 C	3250
Viscosity, Poise @ 25 C	180
Carbon Chain Length	C21+

## **CPAR W-50 Applications:**

Flame retardant and plasticizer in polymers. Flame retardant, plasticizer and lubricant in adhesives, caulks, sealants, and coatings. Additives in lubricants including metalworking fluids. Flame retardant and plasticizer in rubber. Flame retardant and waterproofer in textiles.

www.QualiceLLC.com
11 E.V. Hogan Drive, Hamlet, NC 28345 USA

Qualice, LLC is a true pioneer in the domestic additive manufacturing industry, dedicated to utilizing the newest technology in our production process. At Qualice we are committed to providing the highest quality products with a pledge of uncompromised service. Our entire line of Reliquid products are manufactureed exclusively by Qualice in the USA.